

# PRODUCT INFORMATION SHEET

**PRODUCT NAME:** Epoxy Enamel - Tile Grey

**#:** #375 / 875

---

**PRODUCT DESCRIPTION:** A first class interior / exterior floor enamel. Recommended for balconies, wood, metal and cement floors.

**IDEAL FOR:** Interior / exterior, metal, cement, wood floors.

**FEATURES:** Resistant to spatter during application, flaking and peeling.  
Durable.

**SURFACE PREPARATION:** Make sure surface is clean, dry and free of dirt, wax and grease. Remove any loose, flaking or peeling areas.

- i) Previously Painted Surfaces: Wash with TSP solution and rinse well with water. Lightly sand to create smooth surface.
- ii) Cement: Remove all loose particles with a metal wire brush. First coat to be diluted 10% with mineral spirits.
- iii) New Cement: Acid etch with Muriatic Acid before applying first coat. Rinse well.
- iv) Metal: Remove all rust with a metal wire brush and apply one coat of primer # 1125.

**APPLICATION PROCEDURES:** Brush or Roller application is suitable.

**LIMITATIONS / PRECAUTIONS:** Keep away from ignition sources. Apply when temperatures are between 10°-28°C.

**REDUCTION SOLVENT:** Mineral Spirits.

**CLEAN-UP:** Mineral Spirits.

# TECHNICAL INFORMATION

**PRODUCT NAME:** Epoxy Enamel - Tile Grey  
**#:** 375 / 875

|  |  |
|--|--|
| <b>PRODUCT TYPE:</b>                               | Alkyd  |
| <b>GLOSS:</b>                                      | High Gloss   |
| <b>VISCOSITY:</b>                                  | 75 - 80 Ku   |
| <b>WEIGHT PER US GALLON:</b>                       | 8.65   |
| <b>SOLID BY VOLUME:</b>                            | 43.8 +- 2%   |
| <b>SOLID BY WEIGHT:</b>                            | 56.9 +- 2%   |
| <b>COVERAGE M<sup>2</sup>/L AT 25 MICRONS DFT:</b> | 17.25  |
| <b>COVERAGE SQ. FT./US GALLON AT 1 MIL DFT:</b>    | 703  |
| <b>FLASH POINT:</b>                                | 40°C   |
| <b>VOC (g/L):</b>                                  | 443  |
| <b>DRYING TYPE:</b>                                | Air (Oxidizing)  |
| <b>DRYING TIME:</b>                                |  |
| i) <b>TACK FREE:</b>                               | 4-6 Hours  |
| ii) <b>HARD DRY:</b>                               | 12-15 Hours  |
| iii) <b>RECOAT:</b>                                | 18-24 Hours  |
| <b>STORAGE:</b>                                    | Keep away from ignition sources.<br>Keep out of childrens reach. |

*Note: All information contained in this data sheet is accurate to the best of our knowledge however due to variances in individual surface preparation and application procedures UCP Paint Inc. can not assume responsibility for the results obtained.*